

Application No. 10/772,102

AMENDMENTS TO THE CLAIMS

A detailed listing of all claims that are, or were, in the present application, irrespective of whether the claim(s) remains under examination in the application are presented below. The claims are presented in ascending order and each includes one status identifier. Those claims not cancelled or withdrawn but amended by the current amendment utilize the following notations for amendment: 1. deleted matter is shown by strikethrough for six or more characters and double brackets for five or less characters; and 2. added matter is shown by underlining.

1. (Previously Presented) A method for producing metal/metalloid oxide particles comprising rare earth metals, the method comprising reacting a reactant stream in a gas flow, the reactant stream comprising a rare earth metal precursor and an oxygen source wherein the reaction is driven by energy from a light beam, and wherein the resulting metal/metalloid oxide particles have less than about 10 mole percent of the metal being rare earth metal.
2. (Original) The method of claim 1 wherein the light beam is an infrared laser beam.
3. (Original) The method of claim 1 wherein the reactant stream comprises an aerosol with droplets comprising metal solutions.
4. (Original) The method of claim 3 wherein the metal solutions comprise non-rare earth metal ions and rare earth metal ions.
5. (Original) The method of claim 3 wherein the solution are aqueous solutions.

Application No. 10/772,102

6. (Original) The method of claim 3 wherein the solution comprises nitrate ions.
7. (Original) The method of claim 3 wherein the solution comprises ammonium ions.
8. (Original) The method of claim 1 wherein the reactant stream comprises a non-rare earth metal/metalloid precursor.
9. (Original) The method of claim 8 wherein the rare earth metal oxide particles comprise rare earth doped metal oxide particles.
10. (Original) The method of claim 8 wherein the rare earth metal oxide particles comprise a stoichiometric amount of rare earth metal.
11. (Original) The method of claim 1 wherein the oxygen source comprises O₂.
12. (Original) The method of claim 1 wherein the reactant stream comprises a non-rare earth metal/metalloid selected from the group consisting of aluminum, manganese, silver, yttrium, zinc, magnesium, vanadium, silicon, boron, strontium, and barium.
13. (Original) The method of claim 1 wherein the rare earth metal comprises europium, cerium, terbium, gadolinium, thulium, praseodymium or erbium.
14. (Original) The method of claim 1 wherein the reactant stream further comprises a non-metal composition that absorbs infrared light.

Application No. 10/772,102

15. (Cancelled)
16. (Currently Amended) A method of making a collection of metal/metalloid sulfides particles in a powder with an average particle size of less than about 500 nm, the method comprising contacting metal/metalloid oxide particles in a powder with H_2S or CS_2 at a temperature below the melting temperature of the metal/metalloid oxide particles and the metal/metalloid sulfide particles, wherein the metal/metalloid oxide particles have an average particle size under 500 nm and wherein the powders are stirred.
17. (Original) The method of claim 16 wherein the temperature is less than about $400^{\circ}C$.
18. (Currently Amended) A collection of rare earth doped metal/metalloid sulfide particles having an average particle size from about ~~[[15]]~~ 35 nm to about 250 nm.
19. (Original) The collection of particle of claim 18 comprising ZnS.
20. (Original) The collection of particles of claim 18 wherein the particles comprise no more than about 10 mole percent rare earth metal relative to the total metal composition.
21. (Currently Amended) The collection of particle of claim 18 wherein having an average particle size from about ~~[[15]]~~ 35 nm to about 100 nm.
22. (Previously Presented) The collection of particle of claim 18 wherein essentially no particles have a diameter greater than about 5 times the average particle size.

Application No. 10/772,102

23. (Previously Presented) The collection of particles of claim 18 wherein at least about 95 percent of the particles have a diameter greater than about 40 percent of the average diameter and less than about 225 percent of the average diameter.

24. (Previously Presented) The collection of particles of claim 18 wherein the rare earth metal comprises europium.

25. (Previously Presented) The collection of particles of claim 18 comprising SrS.

26. (Previously Presented) The collection of particles of claim 25 wherein the rare earth dopant comprises Ce.